


## Product Designation

<b>Product Group:</b>	Polyamide machine tapes
<b>Main Industry Segments:</b>	Paper manufacturing and processing
<b>Belt Applications:</b>	Machine tape; Power transmission belt; Thread carrier belt
<b>Special Features:</b>	Abrasion resistant; Constant coefficient of friction; Forgiving in case of short term shock like overloads
<b>Mode of Use/Conveyance:</b>	Declined; Horizontal; Inclined; Power transmission; Vertical

## Product Design (enlarged)



## Product Construction/Design

<b>1 Conveying Side (Material):</b>	Acrylonitrile-Butadiene-Rubber (NBR)
<b>1 Conveying Side (Surface):</b>	Mat (dull finish)
<b>1 Conveying Side (Property):</b>	Adhesive
<b>1 Conveying Side (Color):</b>	Green
<b>2 Traction Layer (Material):</b>	Polyamide (PA)
<b>Number of Fabrics:</b>	2
<b>3 Running Side/Pulley Side (Material):</b>	Polyurethane cross-linked (PUR)
<b>3 Running Side/Pulley Side (Surface):</b>	Blank/smooth
<b>3 Running Side/Pulley Side Property:</b>	Non-adhesive
<b>3 Running Side/Pulley Side (Color):</b>	Black

## Product Characteristics

<b>Slider bed suitable:</b>	Yes
<b>Carrying rollers suitable:</b>	Yes
<b>Troughed installation suitable:</b>	No
<b>Permanently antistatic:</b>	Yes

## Technical Data

<b>Thickness:</b>	1.2 mm	0.05 in.
<b>Mass of belt (belt weight):</b>	1.3 kg/m <sup>2</sup>	0.27 lbs./sq.ft
<b>Pulley diameter (minimum):</b>	40 mm	1.6 in.
<b>Pulley diameter minimum with counter flexion:</b>	40 mm	1.6 in.
<b>Tensile force for 1% elongation (k1% static) per unit of width (Habasit standard 320.064):</b>	6.5 N/mm	37 lbs./in.
<b>Admissible tensile force per unit of width:</b>	8 N/mm	46 lbs./in.
<b>Operating temperature admissible (continuous):</b>	Min -20 °C Max 100 °C	Min -4 °F Max 212 °F
<b>Coefficient of friction of driving pulley of steel:</b>	0.3 [-]	0.3 [-]
<b>Seamless manufacturing width:</b>	1200 mm	47 in.

All data are approximate values under standard climatic conditions: 23°C/73°F, 50% relative humidity (DIN 50005/ISO 554), and are based on the Master Joining Method.

## Additional Technical Information

<b>Chemical Resistance Class:</b>	2 (These indications are not guarantees of properties)
<b>Installation and Handling Instructions:</b>	Do not go below initial tension (epsilon) ~0.5%.; Observe the indications of the machine handbook from the machine manufacturers.
<b>Limitations:</b>	This product has not been tested according to ATEX standards (atmospheres with explosion risk - ATEX 95 regulation or EU directive 94/9) and therefore is subject to user's analysis in the respective environment.

## Legend

*	No calculation Value
1)	No further authoritative acceptance since elimination of prior approval procedure of September 24, 1997, from USDA authority
2)	Product containing different coating materials such as elastomer, natural fibers, silicones, etc., are not subject to the directive 2002/72/EC
8)	Due to high coefficient of friction of running/pulley side, the suitability for use on slider beds is limited
<b>BgVV</b>	Bundesinstitut für gesundheitlichen Verbraucherschutz und Veterinärmedizin (German Federal Institute for Consumers' Health Protection and Veterinary Medicine)
<b>EEC</b>	European Economic Community
<b>EU</b>	European Union (Directive 2002/72/EC)
<b>FDA</b>	Food and Drug Administration
<b>NA</b>	Not available
<b>NAP</b>	Not applicable
<b>USDA</b>	United States Department of Agriculture (Food Safety and Inspection Service, Washington D.C.)

## Product Liability, Application Considerations

If the proper selection and application of Habasit products are not recommended by an authorized Habasit sales specialist, the selection and application of Habasit products, including the related area of product safety, are the responsibility of the customer. All indications / information are recommendations and believed to be reliable, but no representations, guarantees, or warranties of any kind are made as to their accuracy or suitability for particular applications. The data provided herein are based on laboratory work with small-scale test equipment, running at standard conditions, and do not necessarily match product performance in industrial use. New knowledge and experiences can lead to modifications and changes within a short time without prior notice.

**BECAUSE CONDITIONS OF USE ARE OUTSIDE OF HABASIT'S AND ITS AFFILIATED COMPANIES CONTROL, WE CANNOT ASSUME ANY LIABILITY CONCERNING THE SUITABILITY AND PROCESS ABILITY OF THE PRODUCTS MENTIONED HEREIN. THIS ALSO APPLIES TO PROCESS RESULTS / OUTPUT / MANUFACTURING GOODS AS WELL AS TO POSSIBLE DEFECTS, DAMAGES, CONSEQUENTIAL DAMAGES, AND FURTHER-REACHING CONSEQUENCES.**